

## Siniat Finishing Plaster

### Description

Siniat Finishing plaster used as a skimming plaster on plasterboard, cement and bricks.  
Can be used as a jointing compound

### Intended use

Internal use only  
Skimming of walls and ceilings

### Features

It provides ease of application
Single product solution
Easy to mix
High quality finish

### Product Identification

Appearance	Fine white powder
Package	25kg bags (+ 2%)

### Specification

Coverage ratio:	1kg for 1mm of application per m2
Uses	Finishing skim coat to plasterboard, cement rendered and concrete surfaces
Water / plaster ratio:	6.5 – 7 lt. water to 10kg of Siniat Finishing Plaster
Workability:	60 Minutes
Final setting time:	130 Minutes
Setting starts:	20 minutes
Compressive strength:	35 kgf/cm <sup>2</sup> (4x4 block)
Pass 160-micron sieve:	99./5%



**Etex South Africa**, 2 Setchell Road, Roodekop, Gauteng, South Africa.  
**Tel:** +27(0) 11 389 4500 | **Email:** [contactus.etexsa@etexgroup.com](mailto:contactus.etexsa@etexgroup.com) | [www.etexgroup.co.za](http://www.etexgroup.co.za)

**Directors:** S Carter (British), J M Desmoutier (French), J L G Bernard (French)

PASS 45 MICRON SIEVE (minimum)	80%
Bulk density:	750-800 kg/m <sup>3</sup>
Dry density:	950 – 1000 kg/m <sup>3</sup>
Fire classification:	A1 (according to TS EN 13279-1)
Usage temperature:	Between 5° C and 40° C

## Storage:

Siniat Finishing plaster must be stored internally, on a level surface, in a dry place protected from the weather.

## Health & Safety

Please read the Plasters Health and Safety Datasheet available on our website. [www.etexgroup.co.za](http://www.etexgroup.co.za)



**Etex South Africa**, 2 Setchell Road, Roodekop, Gauteng, South Africa.  
**Tel:** +27(0) 11 389 4500 | **Email:** [contactus.etexsa@etexgroup.com](mailto:contactus.etexsa@etexgroup.com) | [www.etexgroup.co.za](http://www.etexgroup.co.za)

**Directors:** S Carter (British), J M Desmoutier (French), J L G Bernard (French)