

# Siniat Premium Jointing Compound

## Description

Siniat Jointing Compound is a jointing compound used together with Siniat Fibatape at the tapered edge joints of Siniat plasterboards.

## Intended use

Internal use only

Used together with Siniat Fibatape on the taper edges of Siniat Plasterboard to join two boards together

## Features

It provides ease of application
Special additives within its body delay the absorption of joint water by the plasterboard surface
It has a filler function which creates a smooth surface finish due to special grain distribution
It has high binding features
It has a flexible feature which eliminates the chance of cracking on the joints and therefore enables the application surface to work uniformly
Since it is a breathing material, it creates a healthy atmosphere by balancing the moisture rate

## Product Identification

Appearance	Fine white powder
Package	<b>20kg bags (+ 2%)</b>
Contents	<b>Calcium sulphate hemihydrate, silicas aggregates and retarder</b>
Coverage per 20kg	<b>Approximately 40 m</b>

## Specification

<b>Water / plaster ratio</b>	6 – 6.5 lt water to 10kg of Siniat Jointing Compound
<b>Workability</b>	60 minutes
<b>Final setting time</b>	130 minutes
<b>Pass 160-micron sieve (min)</b>	99.5%



**Etex South Africa**, 2 Setchell Road, Roodekop, Gauteng, South Africa.  
 Tel: +27(0) 11 389 4500 | Email: [contactus.siniat@etexgroup.com](mailto:contactus.siniat@etexgroup.com) | [www.siniat.co.za](http://www.siniat.co.za)

**Directors:** S Carter (British), J L G Bernard (French)

Pass 45-micron sieve (min)	80%
Bulk density (powder)	750-800 kg/m <sup>3</sup>
Dry density	1050 – 1100 kg/m <sup>3</sup>
Surface hardness	45 shore D

## Storage:

Siniat Finishing plaster must be stored internally, on a level surface, in a dry place protected from the weather.

## Health & Safety

Please read the Plasters Health and Safety Datasheet available on our website. [www.siniat.co.za](http://www.siniat.co.za)



**Etex South Africa**, 2 Setchell Road, Roodekop, Gauteng, South Africa.  
**Tel:** +27(0) 11 389 4500 | **Email:** [contactus.siniat@etexgroup.com](mailto:contactus.siniat@etexgroup.com) | [www.siniat.co.za](http://www.siniat.co.za)

**Directors:** S Carter (British), J L G Bernard (French)